

Hardness Conversion Table / Sertlik Çevrim Tablosu

VICKERS (HV)	BRINELL (HB)	ROCKWELL (HRc)
100	95	-
105	99.8	-
110	105	-
115	109	-
120	115	-
125	119	-
130	124	-
135	128	-
140	133	-
145	138	-
150	143	-
155	147	-
160	152	-
165	156	-
170	162	-
175	166	-
180	171	-
185	176	-
190	181	-
195	185	-
200	190	-
205	195	-
210	199	-
215	204	-
220	209	-
225	214	-
230	219	-
235	223	-
240	228	20.3
245	233	21.3
250	238	22.2
255	242	23.1
260	247	24.0
265	252	24.8
270	257	25.6
275	261	26.4
280	266	27.1
285	271	27.8
290	276	28.5
295	280	29.2
300	285	29.8
310	295	31.0
320	304	32.2
330	314	33.3
340	323	33.4
350	333	33.5

VICKERS (HV)	BRINELL (HB)	ROCKWELL (HRc)
360	342	36.6
370	352	37.7
380	361	38.8
390	371	39.8
400	380	40.8
410	390	41.8
420	399	42.7
430	409	43.6
440	418	44.5
450	428	45.3
460	437	46.1
470	447	46.9
480	(456)	47.7
490	(466)	48.4
500	(476)	49.1
510	(485)	49.8
520	(494)	50.5
530	(504)	51.1
540	(513)	51.7
550	(523)	52.3
560	(532)	53.0
570	(542)	53.6
580	(551)	54.1
590	(561)	54.7
600	(570)	55.2
610	(580)	55.7
620	(589)	56.3
630	(599)	56.8
640	(608)	57.3
650	(618)	57.8
660	-	58.3
670	-	58.8
680	-	59.2
690	-	59.7
700	-	60.1
720	-	61.0
740	-	61.8
760	-	62.5
780	-	63.3
800	-	64.0
820	-	64.7
840	-	65.3